

## MASK 51

**Product Description:** It is resistant against a lot of chemicals and atmospheric factors. The corrosion resistance is high.

**Application Surface:** Metal, Aluminum, Glass, Steel, Plastic, Smooth Surfaces

**Application Type:** 2 components

### Technical Specifications

Density : 1.5 kg/L

Flashpoint : >21°C

Vol. % Solid : 55%

Economy : Ca. 8m<sup>2</sup>/L/60 µm.

Appearance : Matt.

Equipment Cleaning: It should be cleaned with Nitro Cellulosic thinner.

Colour : Grey /004), White (001) and Beige (002).

Application Duration: 5-10 minutes between the layers should be waited.

Expiry Date : the shelf life is 2 years.

Spray Coefficient : 1-3

Film Thickness : 60-180 µm

Drying : 20°C: 3-4 hours every layer.

60°C: 20-30 minutes every layer.

The application can be made on the humid floors at 20°C after 20 minutes.

	<b><u>Nozzle Diameter (mm)</u></b>	<b><u>Application Pressure (bar)</u></b>
Gravity	1,4 – 1,8	3,5 – 4,5
Suction	1,6 – 1,8	3,5 – 4,5

HVLP/LVLP

1,4 – 1,8